()



(11) Publication number:

01218633 A

PATENT ABSTRACTS OF JAPAN

Generated Document.

(21) Application number: 63043567

(51) Intl. Cl.: **B01J 20/22** B01D 53/34

(22) Application date: **26.02.88**

(30) Priority:

(43) Date of application

publication:

31.08.89

(84) Designated contracting

states:

(71) Applicant: JAPAN ATOM ENERG' EBARA CORP

T CYCO MAIZANODII

(72) Inventor: SUGO TAKANOBU

OKAMOTO JIRO FUJIWARA KUNIO SEKIGUCHI HIDEAKI

FUJII TOSHIAKI

(74) Representative:

(54) ACID GAS ADSORBENT

(57) Abstract:

PURPOSE: To remove the effect of carbonic acid gas and enhance the characteristic of selectively removing the other acid gases, by depositing a metallic phthalocyanine on the ion exchanger having a quaternary ammonium group to thereby form an acid gas adsorbent thereon.

CONSTITUTION: An ion exchanger having the anion exchange group represented by at least a quaternary ammonium group as ion exchange group is impregnated into the liquid containing a metallic phthalocyanine dissolved or diffused therein. A metallic phthalocyanine is deposited on this ion exchanger preferably in an amount of 0.05-30wt.% and more preferably 0.10-10wt.% to form an acid gas adsorbent. The ion exchanger made of ion exchange resin into a fibrous form is suitable for this

BEST AVAILABLE COPY

purpose due to its easy fabrication. The ion exchanger thus obtained is remarkably improved in selectivity for hydrogen sulfide, independently of carbonic acid gas.

COPYRIGHT: (C)1989,JPO&Japio

BEST AVAILABLE COPY